

SC 00200

FINIX 80

Technical Sheet

NAME:

FINIX 80

TYPE:

indoor water-based sylossanic finish for indoor and outdoor, high breathable.

USE:

indoor water-based finish to get wash effects and for the decoration of Rococo' Anticando 600, Travertino and o to achieve Art Antique effect the applicator creates with his imagination .

CHARACTERISTICS:

specific weight:

1.025 ± 30 gr/LT. at 20°C

viscosity:

450 cps

yield:

14-15 m²/LT one coating, not coloured, on Rococo' Anticando 600 (it may vary according to the roughness, porosity and surface absorption and to the method of application)

11- 14 m²/LT. one coating, coloured on Rococo' Anticando 600 (it may vary according to the roughness, porosity and surface absorption and to the method of application)

15- 20 m²/LT. one coating, not coloured on Rococo' Travertino (it may vary according to the roughness, porosity and surface absorption and to the method of application)

30- 40m²/LT. one coating, coloured on Rococo' Travertino (it may vary according to the roughness, porosity and surface absorption and to the method of application)

colours:

from the catalogue

packaging:

LT. 0,750

on the surface:

1-2 hours at 20°C

over painting:

8-10 hours at 20°C

below the surface:

24-72 hours at 20°C

DRYING TIME:

CHARACTERISTICS AND RESISTANCE :

FINIX 80 is transparent and to obtain the colours in the catalogue, simply mix FINIX 60 with the appropriate quantity of COLORI' colouring paste, as described under each colour sample. Alternatively the VALCLONE dispensing system can be used

PREPARATION OF THE PRODUCT:

dilution:

ready to use, exceptionally on the second coating of Rococo' Travertino which is to be diluted with water

system:

woollen glove or sponge - brush

number of coating:

1 -2

APPLICATION

FOR ROCOCO ANTICANDO 600 After 8 hours at 20°C , once the product has dried fully, apply one coat of FINIX 80 using the tools as per the effect to achieve . Using Finix 80 other decorative effects are possible to obtain and it can be applied also using a woollen glove or a sponge or even a brush according to the imagination of the applicator.

SC 00200

FOR ROCOCO' TRAVERTINO: when the ROCOCO' TRAVERTINO is completely dry, apply a coat of undiluted transparent FINIX 80 by using a compact sponge on the smooth surface leaving the veining and notching. After 4 hours at 20°C apply a second finishing coat of coloured FINIX 80, with 50% dilution. After this, while FINIX 80 is still wet, remove the excess product on the smooth part using the sponge (which has been washed and well-squeezed), in order to obtain the natural stone effect, due to the different levels of absorption of the surface.

Application temperature: above +10°C and below +30°C. Do not apply under direct sunlight or in windy conditions. Avoid application during very humid days or on frozen surfaces

Storage: make sure that the tin is tightly closed, even after use, and store at a temperature between +5°C and +30°C

Stability: approximately 1 year (2 years for PRIMER 1200 and FINIX 80), if well sealed and never opened.

NOTES:

Mix well before application Wash tools with water and soap immediately after use.

Technical Sheet n° SC 00200 issued by the Control Quality Department:

Edition n° 4

October 2016