

ROCOCO' STUCCO VENEZIANO 1000 LUCIDO DIRETTO

Technical and Environmental Data Sheet

NAME:

ROCOCO' STUCCO VENEZIANO 1000 LUCIDO DIRETTO

TYPE:

mural mineral coating

USE

coatings of high level of transpiration suitable for indoor with glossy effect up to mirror surfaces decorated .

TECHNICAL DATA:

specific weight: 1.750± 30 gr/LT. at 20°C

viscosity: = = =

yield: 7-8 m²/LT. for 2 coatings on smooth surface (it may vary depending on roughness, porosity, absorption surface and application method)

aesthetic effect: glossy

colours: as per Rococo' catalogue

packaging: LT. 1 – LT.4 - LT. 12

on the surface: 3-4 hours at 20 °C

over painting: 24 hours at 20°C

below the surface: 28 days at 20 °C

DRYING TIME:

once the product has hardened completely, a breathable film develops, offering good resistance to knocks and normal abrasion

CHARACTERISTICS AND

RESISTANCE:

ENVIROMENTAL PERFORMANCES

PERFORMANCES	STANDARD RULE	VALUE	BRAND
EMISSION OF INDOOR POLLUTING SUBSTANCES	ISO 16000	TVOC < 1 mg/m ³ A Classe	
ABSENCE OF DANGEROUS SUBSTANCES	-	FREE	
FORMALDEHYDE ISSUE RATE, X	JIS A 1902-3	X < 0.005 mg/m ² h F****	
VOC On product to use	Directive 2004-42-CE	max 26 g/L (Ue Limit 200 g/L) A/1 Cat.	

PREPARATION OF THE SURFACE:

New surfaces: use a suitable filler to repair the surface where necessary. When dry, sand the surface and apply a coat of PRIMER 1200 diluted 15 - 20% with water. After roughly 4 hours at 20°C, apply Rococo' Stucco Veneziano 1000 Lucido Diretto

Old surfaces: remove old peeling or chalking paint and wash using a suitable soap product. Next, apply a coat of PRIMER 1200 diluted 50% with water to act as a fixative. After approximately 4 hours at 20°C, apply a second coat of PRIMER 1200 diluted 20 - 30% with water. However, if the surfaces are sound and not chalking, apply a single coat of PRIMER 1200 diluted 20 - 30% with water.

**PREPARATION OF THE
PRODUCT:
APPLICATION**

APPLICATION CYCLE:

After 4 hours at 20°C, apply Rococo' Stucco Veneziano 1000 Lucido Diretto.
dilution ready to use.

system: stainless steel trowel
number of coatings 2-3

Antique Glossy effect with Rococo' Stucco Veneziano 1000 Lucido Diretto:
apply Rococo' Stucco Veneziano 1000 Lucido Diretto using the PV 43, PV 44 or PV 45 stainless steel trowel and creating a smooth and compact surface. After roughly 6 hours at 20°C, sand the surface thoroughly and then apply Rococo' Stucco Veneziano 1000 Lucido Diretto with irregular strokes 6 - 10 cm long and spaced 4 - 6 cm apart, over the entire surface to be treated.

After roughly 1 hour at 20°C, start again from the beginning of the surface decorated with the first coat, applying strokes as described above but covering the surface so that each stroke partly overlaps those applied previously.

POLISHING AND PROTECTION: When the product is almost dry, rework the surface in all directions by pressing on the surface and continue to apply the product with the trowel until obtaining a glossy or even reflective surface. When Rococo' Stucco Veneziano 1000 Lucido Diretto is almost dry, it should be polished by smoothing it with the spatula or stainless steel trowel, applying pressure to the product with strokes of spatula in all directions, continuing to spatulate until a shiny mirror surface is obtained.

To make Rococo' Stucco Veneziano 1000 Lucido Diretto semi-washable and even more glossy, apply a light coat of Cera Lucidante 370 or Cera Lucidante 420 to the water. When the wax is dry, after about 3 - 4 hours at 20 ° C, the support still remains opaque. To make it brilliant, use a Wool Cloth with rotary movements and exerting pressure on the support, until obtaining the desired gloss.

Application temperature: between +10°C and +30°C.

Storage: make sure that the tin is tightly closed, even after use, and store at a temperature between +10°C and +30°C.

Stability: approximately 2 years in properly sealed containers that are never opened

NOTE:

Mix well before use, Wash the tools with water, immediately after using, with water and soap.

Technical Sheet n° SC 00288 issued by the Control Quality Department:

Edition n. 2 September 2019