

VALPAINT S.p.A. Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY Tel. +39 071 906383 (r.a.) - Fax +39 071 906384 E-mail: info@valpaint.it C.F./P.IVA/R.I. di AN 01108220425 Capitale Sociale € 500.000,00 i.v.

www.valpaint.it

SC 00255

V88 SATINE

Technical and Environmental Sheet

NAME: **V88 SATINE**

TYPE: decorative hydro-enamel for interiors with satin effect.

USE: for internal surfaces, water-repellent and antibacterial paint.

specific weight: (ISO 20111-1) WHITE: 1.350 ± 30 gr./LT. at 20 °C **CHARACTERISTICS:** neutral : 1.290 ± 30 gr./LT. at 20 °C

yield: 10- 12 m²/LT. for 2 coating to cover (it may

vary according to the roughness, surface

absorption and application methods)

aesthetic effect: satiné

stability: 24 months, stock between +5°C and +30°C

colours: white, neutral and NCS INDEX 1950

colours

packaging: LT. 1 - LT. 4- LT. 10 on the surface 2 hours at 20°C 4 - 6 hours at 20°C over painting: in depth: 24 hours at 20°C

CHARACTERISTICS AND RESISTANCE:

DRYING:

Thanks to its formulation, V88 Satinè guarantees high coverage while maintaining a low thickness. It also has antibacterial, water-repellent and ecosustainable characteristics, thanks to the low VOC and Class A + for indoor emissions according to ISO 16000-9. V88 Satinè combines the properties of traditional anti-molds with the innovative technological strength of silver ions, which inhibit the proliferation of bacteria making the surfaces and indoor air sanitized and antiseptic. For this reason, V88 Satinè is ideal for applications in schools, kindergartens, hospitals, rest homes, commercial activities such as beauty centres or hairdressers and public places in general. It has also obtained the HACCP certification according to the UNI 11021: 2002 standard, i.e. it is suitable for applications in all those environments where food is treated, thanks to the high performance of resistance, washability and healthiness. A specific test also certifies their use in environments with humidity higher than 80%.

PERFORMANCE	RULE	VALUE	BRAND
RESISTANCE TO WASHING	UNI 10560 EN 13300	>5000 SUPERWASHABL E Class 1	UNI 10560 - EN 13300 WASHABILITY
ANTIBACTERIAL ATTIVITY	ISO 22196 JIS Z 2801	EFFECTIVE Bacterial Reduction 99%	ISO 22196 - JIS Z 2801 ANTIBACTERIAL
RESISTANCE TO HIGH LEVEL OF HUMIDITY	EN ISO 6270-1	TEXT PASSED	EN ISO 6270-1 +80% 45 HUMIDITY

page 1 of 3

E-mail: info@valpaint.es



VALPAINT S.p.A Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY Tel. +39 071 906383 (r.a.) - Fax +39 071 906384 E-mail: info@valpaint.it C.F./P.IVA/R.I. di AN 01108220425 Capitale Sociale € 500.000,00 i.v.

www.valpaint.it

SC 00255

CHARACTERISTICS AND RESISTANCE:

RESISTANCE TO PARTICULAR WASHING AGENTS	UNI EN ISO 2812-1	RESISTANT TO: CHLOROACTIVE ACID DESCALER, ALKALINE DEGREASER	UNI EN ISO 2812-1 DISINFECTION
DIRT GRIP	UNI 10792	VERY LOW ΔL = 1,8	UNI 10792 4 2 NO DIRT
НАССР	UNI 11021	SUITABLE IN THE FOOD FIELD	UNI 11021 HACCP
GLOSS	EN ISO 2813	20 - 25 GU	

ENVIRONMENTAL PERFORMANCE

GLOSS	EN ISO 2813	20 - 25 GU	
EMISSION OF INDOOR POLLUTING SUBSTANCES	ISO 16000	TVOC < 1 mg/m³ A+ Class	ÉMISSIONS DANS L'AIR INTÉRIEUR
ABSENCE OF HARMFUL SUBSTANCES	-	FREE	IPA APEO FORMALDEIDE AMMONIACA FREE
FORMALDEHYDE EMISSION RATE	JIS A 1902-3	X<0.005mg/m ² h F****	FORMALDEIDE FREE
VOC On product ready to use	2004-42- Directive	max 15 g/L (UE Limit 200 g/L) Cat. A/l	Voc

PREPARATION OF THE **PRODUCTS:** PREPARATION OF THE **SURFACE**

dilution:

To be diluted at 1:5 with water as a fixative To be diluted at 20-30% with water as finish

V88 Satinè can be applied on various substrates such as cement, plaster, plaster, plasterboard, wood, iron and on already painted surfaces as long as they are well anchored to the support.

Evaluate the consistency of the surface by removing any old deteriorated or dusty paints and anything that can create detachment. Apply as a fixative a coat of V88 Satinè already colored and diluted 1: 5 with water. After 4 - 6 hours at 20 ° C, fill small holes, cracks and cracks. To make the absorption uniform, pass the already colored and diluted V88 Satinè 1: 5 with water only over the grouting and then wait another 6-8 hours at 20 ° C.

system: by brush-by roller-by spray

number of coatings: 1 - 2

After 6-8 hours at 20 ° C from the application of V88 Satinè as a fixative, apply V88 Satiné already tinted as a finish, but this time diluted 20 - 30% with water. Between the first and second coat wait at least 4 - 6 hours at 20 ° C.

page 2 of 3

APPLICATION:

PREPARATION OF THE **SURFACE:**

E-mail: info@valpaintme.ae

E-mail: info@valpaint.es





VALPAINT S.p.A. Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY Tel. +39 071 906383 (r.a.) - Fax +39 071 906384 E-mail: info@valpaint.it C.F./P.IVA/R.I. di AN 01108220425 Capitale Sociale € 500.000,00 i.v.

www.valpaint.it

SC 00255

Application temperature: higher than $+10 \,^{\circ}$ C and lower than $+30 \,^{\circ}$ C. Storage: in a tightly closed can, even after use, at temperatures above + 5 ° C and below $+30 \circ C$.

Stability: about 2 years in well-sealed and never opened packages.

NOTES:

Temperature of application and stocking must be between +5°C and +30°C. Keep away from frost. Wash the tools soon after use with water and soap.

Technical Sheet n° SC 00255 issued by the Responsible Quality Control: Edition n° 3 **June 2020**