

FISSATIVO ACRILICO 30 G

Technical and Environmental DataSheet

NAME:

FISSATIVO ACRILICO 30 G

TYPE:

fixative for plasters, fiber cement, conglomerates

USE:

it makes uniform the absorption of very porous supports improving the final painting film making it well anchored to the treated support

TECHNICAL DATA:

specific weight: 1010 ± 30 gr/lt at 25°C (ISO 2811-1)

viscosity = = =

yield: 20 - 24 m²/LT on the product already diluted

(it may vary according to the roughness, surface absorption and application methods)

aesthetic aspect: = = =

colours: white

packaging: 1-4- lt.

DRYING TIME:

on the surface: 2 hours at 20°C




overpainting 8 hours at 20°C

below the surface 12 hours at 20 ° C

CHARACTERISTICS AND RESISTANCE:

consolidating plaster. Isolates and absorbs absorption, maximizes the yield and application productivity of the finishing product. Overpainted with any type of water-based paint.

ENVIROMENTAL PERFORMANCES

PERFORMANCES	STANDARD	VALUE	BRAND
ABSENCE OF DANGEROUS SUBSTANCES	-	FREE	
FORMALDEHYDE ISSUE RATE, X	JIS A 1902-3	X < 0.005 mg/m ² h F*****	
VOC On product to use	Directive 2004-42-CE	max 15 g/L (Ue Limit 30 g/L) A/h Cat.	

PREPARATION OF THE SURFACE:

Cleaning from dust, scrape old poorly anchored paints, patch the damaged plaster, plaster and sand

PREPARATION OF THE PRODUCT:

dilution Fissativo Acrilico 30 G 1 parts
Water 5 parts

APPLICATION:

system: brush, roll or spray

coats: 1

Application temperature: superior to + 5°C and inferior to +30°C. Do not apply in direct sunlight or in windy conditions. Avoid days with high humidity or freezing surfaces.

Storage: make sure the can is tightly closed, even after use, at a temperature no lower than + 5°C and no higher than + 30°C.

SC 00035

Stability: approximately 2 years in well sealed and never opened can.

NOTE:

Mix carefully the product before use. Wash the tools soon after use with water and soap.

Technical Sheet n. SC 00035 issued by the Control Quality Dpt. :

Edition n. 6

September 2022